

DATA Sheet

Steinbeis Script (ISO 80)

Fibre Source	100 % recovered paper (no use of chlorine, chlorine-dioxide or other halogenated bleaching agents in production process)	
Environmental Label	Blue Angel, EU-Ecolabel	
Grammage [g/m ²] (ISO 536)	70 ± 2,5	80 ± 2,5
Moisture [%] (ISO 287)	6,0 ± 0,4	6,0 ± 0,4
Volume [cm ³ /g] (ISO 534)	1,18 ± 0,05	1,18 ± 0,05
ISO Brightness [%] (ISO 2470, D65_10°)	80,0 ± 2,5	80,0 ± 2,5
CIE Whiteness (ISO 11475, D65_10°)	85,0 ± 2,5	85,0 ± 2,5
Opacity [%] (ISO 2471)	> 90	> 90
Writing properties by ink (DIN 53126)	yes	yes

DATA Sheet

Steinbeis Script (ISO 90)

Fibre Source	100 % recovered paper (no use of chlorine, chlorine-dioxide or other halogenated bleaching agents in production process)						
Environmental Label	Blue Angel, EU-Ecolabel						
Grammage [g/m ²] (ISO 536)	58,0 ± 2,5	68,0 ± 2,5	70,0 ± 2,5	78,0 ± 2,5	80,0 ± 2,5	90,0 ± 2,5	100,0 ± 2,5
Moisture [%] (ISO 287)	6,0 ± 0,4	6,0 ± 0,4	6,0 ± 0,4	6,0 ± 0,4	6,0 ± 0,4	6,0 ± 0,4	6,0 ± 0,4
Volume [cm ³ /g] (ISO 534)	1,18 ± 0,05	1,18 ± 0,05	1,18 ± 0,05	1,18 ± 0,05	1,18 ± 0,05	1,18 ± 0,04	1,18 ± 0,05
ISO Brightness [%] (ISO 2470, D65_10°)	90,0 ± 2,5	90,0 ± 2,5	90,0 ± 2,5	90,0 ± 2,5	90,0 ± 2,5	90,0 ± 2,5	90,0 ± 2,5
CIE Witheness (ISO 11475, D65_10°)	110,0 ± 2,5	110,0 ± 2,5	110,0 ± 2,5	110,0 ± 2,5	110,0 ± 2,5	110,0 ± 2,5	110,0 ± 2,5
Opacity [%] (ISO 2471)	> 90	> 90	> 90	> 90	> 90	> 90	> 90
Writing properties by ink (DIN 53126)	yes	yes	yes	yes	yes	yes	yes