

DATA Sheet

Steinbeis Script (ISO 80)

Fibre source	100 % recovered paper. (paper for deinking) (no use of chlorine, chlorine-dioxide or other halogenated bleaching agents)	
Environmental Label	Blue Angel, EU-Ecolabel	
Grammage [g/m ²] (ISO 536)	70 ± 2.5	80 ± 2.5
Moisture [%] (ISO 287)	6.0 ± 0.4	6.0 ± 0.4
ISO Brightness [%] (ISO 2470, D65_10°)	80.0 ± 2.5	80.0 ± 2.5
CIE Whiteness (ISO 11475, D65_10°)	85.0 ± 2.5	85.0 ± 2.5
Opacity [%] (ISO 2471)	> 80	> 80
Writing properties by ink (DIN 53126)	yes	yes

DATA Sheet

Steinbeis Script (ISO 90)

Fibre Source	100 % recovered paper. (paper for deinking) (no use of chlorine, chlorine-dioxide or other halogenated bleaching agents)				
Environmental Label	Blue Angel, EU-Ecolabel				
Grammage [g/m ²] (ISO 536)	58 ± 2.5	68 ± 2.5	70 ± 2.5	78 ± 2.5	80 ± 2.5
Moisture [%] (ISO 287)	6.0 ± 0.4	6.0 ± 0.4	6.0 ± 0.4	6.0 ± 0.4	6.0 ± 0.4
ISO Brightness [%] (ISO 2470, D65_10°)	90.0 ± 2.5	90.0 ± 2.5	90.0 ± 2.5	90.0 ± 2.5	90.0 ± 2.5
CIE Whiteness (ISO 11475, D65_10°)	110.0 ± 2.5	110.0 ± 2.5	110.0 ± 2.5	110.0 ± 2.5	110.0 ± 2.5
Opacity [%] (ISO 2471)	> 80	> 80	> 80	> 80	> 80
Writing properties by ink (DIN 53126)	yes	yes	yes	yes	yes